



TECHNICAL DATA SHEET

PRODUCT: POLYVINE DECORATORS VARNISH

PRODUCT DESCRIPTION

A Clear Acrylic Coating specially formulated to protect a wide range of surfaces.
Water-resistant, stain resistant, heat resistant, and vapour permeable.
To seal and protect wallpaper, emulsion/latex, plaster, fabrics, decorative paint finishes.

SURFACE PREPARATION

Ensure the surface to be coated is clean and free from grease, wax or polish

APPLICATION

Gloss or Satin: Apply 2-3 coats.
Deadflat: Apply 1-2 coats.
Dilute 10% with water to prime porous surfaces.
By good quality synthetic brush, recommended, or by conventional spray or High Volume Low-pressure spray.
Rollers are not recommended, stippling may occur. Stir well.
If cissing occurs, rub onto affected area with a damp cloth to break the surface tension and re-apply.

CAUTION

Apply dead flat finish sparingly and brush out well, over application could result in misting.
Test dead flat finish for misting over dark colours.
When applied over emulsion/latex paint, it is possible that Decorators Varnish can draw certain stains through the paint, which would not otherwise be visible.
Do not apply over uncured oils.

COVERAGE

Approx. 10-20 sq. m per litre. 108-215 sq. ft per US qt.

CLEAN UP

Any equipment used can be cleaned using soap and water before the clear coat dries. Wipe any excess off surfaces with a damp cloth. Any dried deposits will need a paint stripper to remove them.C

HEALTH AND SAFETY

In case of: skin contact –wash off with soap and water before the clear coat dries. For

people with delicate skin it is advisable to wear gloves.

Eye contact – rinse with clean water for 15 minutes, seek medical attention if irritation persists.

Inhalation - Decorators Varnish does not give off harmful vapours, however it is better to work in well ventilated areas. If there is irritation or an allergic reaction remove the victim to fresh air, and if irritation persists seek medical attention.

Ingestion - Give victim a drink of water and seek medical attention.

FILM PROPERTIES

SHEEN LEVEL: Gloss, Satin, Dead Flat

DRYING TIME: 1 to 2 Hours @ 20°C / 70°F

Low temperature/high humidity increases drying time.

CURE TIME: Up to 5 days @ 20°C / 70°F

RECOAT TIME: Up to 2 Hours @ 20°C / 70°F

FLAMABILITY NONE: before or during use, or in the cured state.

RESISTANT TO: Water and abrasion.

CONTAINERS

500ml, 1L, 2L, 4L. US pint, US Quart, US gal. plastic containers

STORAGE

Store in unopened containers in a cool dry place away from direct sunlight.

The information supplied herein is accurate to the best of our knowledge. Since conditions and methods are beyond our control, no warranty is expressed or implied. You are advised to access the suitability of the product on a test area before application

Further information may be obtained from:

POLYVINE LIMITED

Severn Distribution Park
Sharpness, Berkeley,
Gloucestershire.
GL13 9UQ
United Kingdom

Telephone No. 0845 017 1671

International +44 845 017 1671

Fax: 0845 017 1670

Email info@polyvine.co.uk

Date of issue: October 2005